

CLAIMS:

1. A conductive fluoro-resin composition comprising  
(A) 100 parts by weight of a reactive fluorinated  
5 polyether compound comprising fluorinated polyether units  
and having at least two aliphatic unsaturated hydrocarbon  
radicals in a molecule,  
(B) a compound having at least two hydrogen atoms each  
directly attached to a silicon atom in a sufficient amount  
10 to give 0.4 to 10 equivalents of the silicon atom-attached  
hydrogen atoms relative to the aliphatic unsaturated  
hydrocarbon radicals in component (A),  
(C) a sufficient amount of a platinum group metal  
catalyst to promote reaction between components (A) and (B),  
15 and  
(D) 50 to 2,000 parts by weight of silver particles.
2. The conductive fluoro-resin composition of claim 1  
wherein the reactive fluorinated polyether compound (A)  
20 comprises fluorinated polyether units of the following  
structural formula (1):
- $$-(Rf-O)_q- \quad (1)$$
- 25 wherein Rf is a straight or branched chain perfluoroalkylene  
radical having 1 to 6 carbon atoms, and q is an integer of 1  
to 500.
3. The conductive fluoro-resin composition of claim 1  
30 wherein the silver particles (D) contain at least 10% by  
weight of dendrite or flake shaped silver particles based on  
the loading of the silver particles.
4. The conductive fluoro-resin composition of claim 3  
35 wherein the silver particles (D) have been surface treated  
with an organopolysiloxane or fluorinated polyether  
compound.

5. The conductive fluoro-resin composition of claim 4 wherein said organopolysiloxane is a hydrosilylated organopolysiloxane having at least one hydrogen atom directly attached to a silicon atom.

5

6. The conductive fluoro-resin composition of claim 4 wherein said organopolysiloxane contains up to 500 ppm of non-functional low molecular weight organopolysiloxanes having 3 to 10 silicon atoms.

add.  
A

20250726